

TECHNICAL DATA SHEET
YIPIN[®] ANTI-CORROSION PIGMENT
Aluminium Triphosphate SAP-1



Edition of	2006-12-11
Type	Anti-corrosion Pigment
Delivery Form	White powder
Chemical Class	AlH ₂ P ₃ O ₁₀ · 2H ₂ O(≥60.0%)
Color Index	
CAS No.	13530-50-2
Use Recommendation	Oil

COLOR VALUES AND TINTING STRENGTH

Reference SAP-1 Standard:

TECHNICAL DATA

	<u>Min</u>	<u>Max</u>	<u>Test Method</u>
Water-Soluble Content [%]		1.0	DIN EN ISO787 Part 3 (1995)
Sieve Residue (0.045mm) [%]		0.15	DIN 53195(1990)
PH Value	4.5	6.5	DIN EN ISO787 Part 9 (1995)
P ₂ O ₅ [%]	42.5		Q/GHT150-2004-4.7
Al ₂ O ₃ [%]	10.5		Q/GHT150-2004-4.8
Free Moisture Content [%]		2.0	DIN EN ISO 787 Part 2 (1995)
Oil Absorption [g/100g]	40.0	50.0	DIN EN ISO787 Part 5 (1995)
Whiteness [%]	90.0		Q/GHT150-2004-4.2

STANDARD PACKAGING 25kg/bag

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

YIPIN PIGMENTS, INC. Tel:+1-909-243-7394 Fax:+1-909-243-7397 www.yipin.com
一品颜料 Tel:+86-21-5950 8509 Fax: +86-21-5950 7893 wh@yipin.com

TECHNICAL DATA SHEET
YIPIN[®] ANTI-CORROSION PIGMENT
Aluminium Triphosphate SAP-1



SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handling, product safety and ecology.

This information is given in good faith, without warranty. It also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery.